

SeaRox® SL 640

SeaRox SL 640 is a semi-rigid slab made of stone wool. The product can be supplied with reinforced alu foil or glass cloth.



Application

SeaRox SL 640 is primarily used as part of approved A constructions for Deck and Bulkhead.

Product properties

Properties	Performance		Norm
Thermal conductivity	T (°C) λ (W/mK)	10 0,035	EN 12667
Nominal density	130 kg/m ³		EN 1602 / IMO
Compressive strength	-		EN 826
Fire classification	Non-combustible Approved for A constructions Low Flame-Spread Properties		Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m ²		EN 1609 AC
Max. Application Temperature	Wool: 750°C Facing: 80°C		-
Sound absorption directly mounted	$\alpha_w = 0,80$ Thickness: 50 mm	$\alpha_w = 0,90$ Thickness: 2x30 mm	ISO 354 (approximated) Evaluated after ISO 11 654
Facings (on request)	Reinforced alu foil White glass cloth 210 g/m ² (GW200)		IMO A.653(16) (low flame - spread)

Dimensions

SeaRox SL 640

Thickness (mm): 30-100 mm Length (mm): 1000 mm Width (mm): 600 mm

SeaRox SL 640 ALU

Thickness (mm): 30, 40, 50 mm Length (mm): 1000 mm Width (mm): 600 mm


SeaRox SL 640 GW 200

Thickness (mm): 30, 40, 50 mm Length (mm): 1000 mm Width (mm): 600 mm

Local variations in standard dimensions might occur.

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.



0575



0097