

ProRox® GR 903



ProRox GR 903 is a stone wool insulation product in granulated form.

Application

This product is especially suitable for the thermal and acoustic insulation of cold boxes and air separation plants. It can also be used for insulation of high-temperature industrial applications, such as voids.

Product properties

Properties	Performance											Norms
Thermal conductivity *	T (°C)	-150	-100	-50	0	50	100	200	300	400	500	
	λ (W/mK)	0,021	0,026	0,032	0,038	0,045	0,052	0,068	0,087	0,107	0,129	EN 12667
Reaction to fire	Euroclass A1											EN 13501-1
Corrosion resistance	Trace quantity of water leachable chloride ions: ≤ 10 mg/kg											EN 13468

(*) Stuffing density 170 kg/m³.

Compliance

- ProRox GR 903 complies with the requirements as set by recognized standards like AGI Q 118 and plant specifications.
- ROCKWOOL stone wool insulation is made from volcanic rock and complies with Note Q, regulation (EC) No. 1272/2008

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.